

Vertical Flammability – 12 Second Ignition (FAR 25.853 Appendix F (a) (1) (ii) – 1995)

Applicable to products that are constructed of materials not covered in subparagraph (iv) of FAR 25.853:

- Floor coverings, floor panels of Class B, C, D, or E cargo or baggage compartments
- Textiles (including draperies and upholstery), decorative and non-decorative coated fabrics,
- Seat cushions, padding,
- Leather,
- Trays and galley furnishings,
- Electrical conduit,
- Thermal and acoustical insulation and insulation covering,
- Air ducting, joints and edge covering, and trim strips (decorative and chafing)
- Liners of Class B and E cargo or baggage compartments, insulation blankets,
- Cargo covers and transparencies, molded and thermoformed parts.

Requirements:

- Must be self-extinguishing when tested vertically in accordance with Appendix F.
- The average burn length may not exceed 8 inches and the average flame time after removal of the flame source may not exceed 15 seconds.
- Drippings from the test specimen may not continue to flame for more than an average of 5 seconds after falling.

AWTA Test Code T17A (FAR-B)

Sample required Length direction: 3 specimens: 2" x 12" (50.8mm x 304.8mm)
 Width direction: 3 specimens: 2" x 12" (50.8mm x 304.8mm)

Company name	
Company address	
Contact person	
Contact person email	
Contact person phone number	
Name of your product	
Description of your product	
End use of your product	

Delivery Address	Further information
AWTA Product Testing Level 1, 191 Racecourse Rd, Flemington VIC 3031, Australia	AWTA Product Testing Phone: (03) 9371 2400 Email: producttesting@awta.com.au

IMPORTANT NOTE: [That by submitting samples for testing YOU AGREE that the resulting testing shall be performed under our terms and conditions for testing and consulting services: www.awtaproducttesting.com.au/index.php/about/terms-and-conditions](http://www.awtaproducttesting.com.au/index.php/about/terms-and-conditions)